

GUANTE JUBA - 5200 HEAT STOP


Seamless Kevlar® terry-loop glove



Distributed by:



NORMATIVE



FEATURES

- Flexible and lightweight.
- Air permeable.
- Comfortable.
- Terry loop Kevlar® construction for an outstanding heat and cut protection.
- Elastic knit wrist.
- Enhanced heat contact protection due to its cotton lining.

USES

- Metallurgy.
- Glazery.
- Steel sector.
- Up to 200° cut and heat contact protection.

MORE INFO

Colour	Thickness	Length	Sizes	Packaging
Yellow	1.80 mm	XL - 27 cm	10/XL	1 pairs/package 50 pairs/box

NORMATIVAS

	A - Flame behaviour The material should comply with the requirements in the table. In addition, the material should not drip or melt. The seams should not open up after 15 seconds ignition time.			B - Heat per contact: The material should comply with:
	Service provision level 1	Post-inflammation time ≤ 20	Post-incandescence time No requirement	

2	≤ 10	≤ 120
3	≤ 5	≤ 60
4	≤ 2	≤ 5

Service provision level	Contact temperature(°C)	Threshold time (s)
1	100	≥ 15
2	250	≥ 15
3	350	≥ 15
4	500	≥ 15

Convective heat

The material should comply with:

Service provision level	Hti heat transfer index
1	≥ 4
2	≥ 7
3	≥ 10
4	≥ 18

Service provision level	Heat transfer index t ₃
1	≥ 7
2	≥ 20
3	≥ 50
4	≥ 95

Service provision level	Number of droplets
1	≥ 10
2	≥ 15
3	≥ 25
4	≥ 35

Service provision level	Molten iron (g)
1	30
2	60
3	120
4	200

D - Radiating heat

The material should comply with:

E - Small splashes

The number of droplets necessary to produce a 40°C rise in temperature should meet requirements in the table:

F - Large splashes

The PVC film that simulates the skin will not be smoothed or its surface roughness changed in any other way, with any of the quantities of iron used:


EN388:2016



EN388:2016 Protective gloves against mechanical risks.

The EN388: 2003 standard is renamed EN388: 2016, the year of its revision. The reason for the modification is given by the discrepancies in the results between laboratories in the knife cut test, COUP TEST. Materials with high levels of cut produce a dulling effect on the circular blades, which undermines the result.

The new regulation was published in November 2016 and the previous one is from the year 2003. During these 13 years, there has been a great innovation in the materials for the manufacture of cutting gloves, they have forced to introduce changes in the tests to be able to measure with more rigorous levels of protection. If you want to know more about the main changes in these regulations, you can consult it through our website www.jubappe.es



- A - Abrasion resistance (X, 0, 1, 2, 3, 4)
- B - Blade Cut Resistance (X, 0, 1, 2, 3, 4, 5)
- C - Tear resistance (X, 0, 1, 2, 3, 4)
- D - Puncture resistance (X, 0, 1, 2, 3, 4)
- E - Cutting by sharp objects ISO 13997 (A, B, C, D, E, F)
- F - Impact test complies / does not comply (It is optional. If it complies, put P)

Distributed by:



En388:2016 performance levels	1	2	3	4	5
6.1 abrasion resistance (cycles)	100	500	2000	8000	-
6.2 blade cut resistance (index)	1,2	2,5	5	10	20
6.4 tear resistance (newtons)	10	25	50	75	-
6.5 puncture resistance (newtons)	20	60	100	150	-

Eniso13997:1999 performance levels	A	B	C	D	E	F
6.3 tdm: cut resistance (newtons)	2	5	10	15	22	30

Distributed by:

