


# GUANTE GUANTES DE NITRILO JUBA - 5519 AGILITY DRY

Seamless nylon® and elastane glove with palm dipped coating, a nitrile inner layer and a water based TPU outer layer with T-touch® technology.



**Distributed by:**



## NORMATIVE



## CHARACTERISTICS

- Optimum grip in oily environments thanks to its double nitrile coating with t-touch® technology.
- Extra light.
- Very flexible.
- Excellent breathability.
- Extra comfort.
- Great abrasion resistance that provides a superior durability.
- Environmentally friendly glove, it is manufactured without DMF.

## WORKING GLOVES SUITABLE FOR:

- Mechanical workshops
- Oiled pieces handling
- Automotive industry
- Precise assembly and maintenance
- Wood industry

## MORE INFO

Materials	Colour	Thickness	Length	Sizes	Packaging
Nitrile	Grey / Black	Gauge 15	XS - 22 cm S - 23 cm M - 24 cm L - 25 cm XL - 26 cm XXL - 27 cm	6/XS 7/S 8/M 9/L 10/XL 11/XXL	10 pairs/package 120 pairs/box

## NORMATIVAS


### EN388:2016



#### EN388:2016 Protective gloves against mechanical risks.

The EN388: 2003 standard is renamed EN388: 2016, the year of its revision. The reason for the modification is given by the discrepancies in the results between laboratories in the knife cut test, COUP TEST. Materials with high levels of cut produce a dulling effect on the circular blades, which undermines the result.

The new regulation was published in November 2016 and the previous one is from the year 2003. During these 13 years, there has been a great innovation in the materials for the manufacture of cutting gloves, they have forced to introduce changes in the tests to be able to measure with more rigorous levels of protection. If you want to know more about the main changes in these regulations, you can consult it through our website [www.jubappe.es](http://www.jubappe.es)



A - Abrasion resistance (X, 0, 1, 2, 3, 4)  
B - Blade Cut Resistance (X, 0, 1, 2, 3, 4, 5)  
C - Tear resistance (X, 0, 1, 2, 3, 4)  
D - Puncture resistance (X, 0, 1, 2, 3, 4)  
E - Cutting by sharp objects ISO 13997 (A, B, C, D, E, F)  
F - Impact test complies / does not comply (It is optional. If it complies, put P)

En388:2016 performance levels	1	2	3	4	5
6.1 abrasion resistance (cycles)	100	500	2000	8000	-
6.2 blade cut resistance (index)	1,2	2,5	5	10	20
6.4 tear resistance (newtons)	10	25	50	75	-
6.5 puncture resistance (newtons)	20	60	100	150	-

Eniso13997:1999 performance levels	A	B	C	D	E	F
6.3 tdm: cut resistance (newtons)	2	5	10	15	22	30

**Distributed by:**

