

**POTSDAM - pile jacket**

**Description**

- 1 breast pocket,
- 2 wide front pockets with YKK® zip,
- 2 internal pockets,
- front opening with YKK® zip,
- hood,
- reinforced elbows.

**POTSDAM**



Distributed by:

**Maintenance**

Maximum wash temperature: 40°C; Do not bleach; Do not dry clean; Do not dry in a tumble dryer; Do not iron.



**Item**

V130-0-02 navy  
V130-0-03 clay brown  
V130-0-04 anthracite  
V130-0-05 black



**Standards**

EN ISO 13688:2013

**Sizes**

S – 4XL

**SAFETY TECHNICAL SPECIFICATIONS**

	Test method	description	Cofra result	minimum requirement / range
<b>Background and colour insert fabric</b>	EN ISO 1833-1977, SECTIONE 10	Composition :	100% polyester + COFRA-TEX membrane	
	EN ISO 12127:1996	Weight per unit area	340 g/mq	
	EN 343 paragraph 4.6 ISO 5077-2007	Dimensional Stability To Washing	Warp: -1,4% Weft: -0,4%	+/- 3%
	EN343 clause 4.4 (EN ISO 13934-1)	Tensile strength	Warp : 426.8 N Weft: 634.8 N	Warp: 400 N tensile/mass: >=2 Weft: 400 N tensile/mass: >=2
	EN343 clause 4.5 (EN ISO 4674)	Tear resistance	Warp: 64 N Weft: 26.6 N	Warp: 25 N Weft: 25 N
	EN 343 clause 4.3 (EN 31092)	Water vapour resistance Ret [m <sup>2</sup> Pa/W]	19 (class 3)	class 1: Ret>40 class 2: 20<Ret<40 class 3: Ret<=20
	EN343 clause 4.2 (EN 20811)	Water penetration resistance - Wp [Pa] (before each pretreatment)	>13000 Pa	class1 : Wp >= 8000 Pa class2 : no test required class3 : no test required
	EN343 clause 4.2 (EN 20811)	Water penetration resistance - Wp [Pa] (after each pretreatment)	>13000 Pa (class3)	class1 : no test required class2 : Wp>= 8.000 Pa class3 : Wp >= 13.000 Pa
	ISO 105-X12	Colour fastness to rubbing	Dry: 4-5 Wet: 4	Dry: 4 Wet: 4

## TECHNICAL SHEET

ISO 105-E04	Colour fastness to perspiration	Colour change: 4 - 5 Staining: 4 - 5	Colour change: 4 Staining: 3
ISO 105-C06	Colour fastness to washing ( 40° C)	Colour change: 4 - 5 Staining: 4 - 5	Colour change: 3 - 4 Staining: 4 - 5
EN ISO 13688:2013 par. 4.2 (EN 1413)	The PH's determination from the watery extract	pH 7.0	3,5<PH≤9,5
EN ISO 13688:2013 par. 4.2 (prEN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
ISO 105 B02	Colour fastness to Light	4	4 - 5
ISO 105 – N01	Colour Fastness To Bleaching : hypochlorite	Colour change: 4 - 5	Colour change: 4 - 5
ISO 12945-1:2000	Pilling Resisance	After 18000 revolutions Rating: 4	Rating: 1-5
ISO 12947-2	Abrasion Resistance Martindale test	> 30000	> 30000

Distributed by:

