

# **PASHINO – padded jacket**

## Description

- 2 front pockets with zip,
- 2 internal pockets,
- front opening with zip,
- adjustable foldaway hood,
- elasticated cuffs



## Maintenance

Maximum wash temperature: 30 °C; Do not bleach; Do not dry clean; Do not dry in a tumble dryer; Do not iron.



## Item

V358-0-02 (navy/yellow)  
V358-0-04 (anthracite/orange)  
V358-0-05 (black/lime)  
V358-0-08 (green/rust)

## Standards:

EN ISO 13688:2013

## Sizes

S - 3XL

## SAFETY TECHNICAL SPECIFICATIONS

	Test method	Description	Cofra result	Minimum requirement / range
<b>Background fabric</b>	EN ISO 1833-1977, SECTION 10	Composition:	100% polyester polyurethane coated	
	EN ISO 12127:1996	Fabric mass per unit area	120 g/m <sup>2</sup> ±5%	
	EN ISO 13688:2013 5.3 (ISO 5077)	Dimensional change	warp: -0.1% weft: 0%	±3%
	EN ISO 13688:2013 4.2 (EN 1413)	The PH's determination from the watery extract	pH=6,0	3,5 ≤pH≤ 9,5
	EN ISO 13688:2013 4.2 (EN 14362-1)	Search of the aromatic and carcinogenic amines	Not recording	≤30 ppm
	ISO 105-X12	Colour fastness to rubbing <i>Staining:</i>	Dry 4-5	1 - 5
	ISO 105-C06	Colour fastness to Laundering at 40°C <i>Colour change</i> <i>Staining:</i> diacetate cotton nylon polyester acrylic wool	4-5 4-5 4-5 4-5 4-5 4-5	1 - 5

**Distributed by:**



	ISO 105 E04	Colour fastness to perspiration	Acid	Alkaline	
		Colour change	4-5	4-5	1 - 5
		Staining:			
		diacetate	4-5	4-5	
		cotton	4-5	4-5	
		nylon	4-5	4-5	
		polyester	4-5	4-5	
		acrylic	4-5	4-5	
		wool	4-5	4-5	
	ISO 105-B02	Colour fastness to light			1-5
		Colour change	3		
	ISO 15496	Measurement of permeability to water vapor of textiles	12529.6 (g/m <sup>2</sup> x 24h)		
	ISO 1421	Tensile strength	warp: 930 N weft: 400 N		
	ISO 4674-1	Tear resistance of coated or laminated fabrics	warp: 116 N weft: 133 N		
	ISO 12947-2	Determination of the abrasion resistance of fabrics by the Martindale method (12Kpa)	>20000 cycles		
	EN 20811	Water penetration resistance - Wp [Pa] (before each pretreatment)	Wp > 13000 Pa	CLASS 1 CLASS 2 CLASS 3	Wp ≥ 8000 Pa no test required no test required
Lining	EN ISO 1833-1977, SECTION 10	Composition:	100% polyester		
Padding	EN ISO 1833-1977, SECTION 10	Composition:	100% polyester		
	EN ISO 12127:1996	Fabric mass per unit area	250 g/mq		

**Distributed by:**

